

# Advanced Barrier Coatings<sup>™</sup>





## **VERSATHANE POUR AND ROLL GRADE**

Issue No.01 Sep 2016
Page 1 of 2

PRODUCT DESCRIPTION

A self-levelling solvent free urethane floor coating. Highly resistant to a wide range of oils and chemicals. Extremely abrasion resistant,

INTENDED USES

For the protection of Steel and Concrete, decks, floors etc. High mechanical strength and suitable for industrial environments.

TECHNICAL INFORMATION

Colour Grey (18 B 21) Blue (18 E 53) additional colours available

Finish Semi-gloss

Curing Agent Versathane Hand Applied Activator

Mix Ratio 3 parts Base: 1 part Activator by volume

Specific Gravity Base: 1.30 Activator: 1.22 Mixed: 1.28

Volume Solids 100%

Recommended Film Thickness 1.0 - 2.0 mm depending on service conditions.

Theoretical Spreading Rate 1 m<sup>2</sup>/ litre @ 1000µm

Application Method Brush, Roller,

Re-coat After 2 hours and within 24 hours of initial application.

Drying Times at 20°C Touch Dry 2 hours Hard Dry 8 hours

Full Cure at 20°C 7 days

SURFACE PREPARATION

## Steel:

Ensure surfaces are free from contamination. Abrasive blast with grit to minimum BS 7079 standard SA 2  $\frac{1}{2}$  surface profile depth 75-100 microns.

Mechanical tools may also be used providing a surface profile of minimum 75 microns can be achieved. Do not polish/burnish the steel surface.

#### Concrete:

Remove all laitance and other contaminants by blast cleaning. Ensure the concrete is dry to a reading of less than 10% moisture. Seal with Versathane LV Sealer.

The temperature of the substrate must be at least 3°C above the dew point during application and relative humidity below 80%.



## Advanced Barrier Coatings<sup>™</sup>





## **VERSATHANE POUR AND ROLL GRADE**

Issue No.01 Sep 2016
Page **2** of **2** 

#### **APPLICATION**

Add hardener to base and stir thoroughly to a uniform mix. Ensure all material on the sides and bottom of the container are fully incorporated. Decant into a plastic bucket and re-stir prior to application. Apply evenly by brush or roller to the required film thickness. The wet coating should be de-aerated with a porcupine roller.

Use product within stated Pot Life 20 – 25 minutes at 20°C

Cleaning solvent. All equipment must be cleaned thoroughly immediately after use with Pracsolv 1

### **REGULATORY DATA**

Packaging Supplied in 4 litre and 20 litre composite packs

Flash Point 200°C

VOC 0 g/litre

Shelf life: 24 months from date of manufacture when stored in the original sealed containers at 20°C.

## SAFETY PRECAUTIONS

Refer to the product Material Safety Data Sheet supplied by Advanced Barrier Coatings Ltd. Ensure all waste materials and empty containers are disposed of in accordance with local regulations.

### **Disclaimer**

The information given in this technical data sheet - whether verbal, or in writing is for guidance only and is given in good faith, but without warranty. This also applies where proprietary rights or third parties are involved. Any person using Advanced Barrier Coatings Ltd products without first making further enquiries as to the suitability of the products for the intended purpose and testing the products to assess their fitness for the purpose does so at their own risk. The application and surface preparation are beyond our control and are therefore your own responsibility, and we can accept no liability for the performance of the products arising out of such use. The information contained in this data sheet is liable to modification at any time and It is the user's responsibility to ensure that this sheet is current prior to using the product.